



SentryGlas® Plus Elastic Properties (SGP 5000)

DuPont Glass Laminating Solutions

*The preferred supplier and innovator
of glass laminating solutions
for a better, safer world*



The miracles of science™

Polymer Interlayer Behavior

All interlayers are viscoelastic

- Stiffness (modulus) and Poisson ratio vary as a function of temperature and load duration (creep)
- Evaluate properties over a range of test temperature and time using dynamic mechanical analysis and creep tests (ASTM D 4065)
- “Small” strain values (< 20 % engineering strain)

Young’s modulus, E , shear modulus, G , & Poisson ratio, ν .

- Extract E , G and ν for specified temperature and load duration
- Choose appropriate elastic property values for design case and assign to an effective elastic interlayer
- Important to assess the likelihood of achieving full design load at the design temperature and load duration

Young's Modulus: SentryGlas® Plus

Young's Modulus E (MPa)		Load Duration						
		1 s	3 s	1 min	1 hr	1 day	1 mo	10 yrs
Temperature	10 °C	692.	681.	651.	597.	553.	499.	448.
	20 °C	628.	612.	567.	493.	428.	330.	256.
	24 °C	581.	561.	505.	416.	327.	217.	129.
	30 °C	442.	413.	324.	178.	148.	34.7	15.9
	40 °C	228.	187.	91.6	27.8	13.6	9.86	8.84
	50 °C	108.	78.8	33.8	12.6	8.45	6.54	6.00
	60 °C	35.3	24.5	10.9	5.10	3.87	3.24	2.91
	70 °C	11.3	8.78	5.64	2.52	1.77	1.44	1.35
	80 °C	4.65	3.96	2.49	0.96	0.75	0.63	0.54

Shear Modulus: SentryGlas® Plus

Shear Modulus G (MPa)		Load Duration						
		1 s	3 s	1 min	1 hr	1 day	1 mo	10 yrs
Temperature	10 °C	240.	236.	225.	206.	190.	171.	153.
	20 °C	217.	211.	195.	169.	146.	112.	86.6
	24 °C	200.	193.	173.	142.	111.	73.2	43.3
	30 °C	151.	141.	110.	59.9	49.7	11.6	5.31
	40 °C	77.0	63.0	30.7	9.28	4.54	3.29	2.95
	50 °C	36.2	26.4	11.3	4.20	2.82	2.18	2.00
	60 °C	11.8	8.18	3.64	1.70	1.29	1.08	0.97
	70 °C	3.77	2.93	1.88	0.84	0.59	0.48	0.45
	80 °C	1.55	1.32	0.83	0.32	0.25	0.21	0.18

Poisson Ratio: SentryGlas® Plus

Poisson Ratio, ν		Load Duration						
		1 s	3 s	1 min	1 hr	1 day	1 mo	10 yrs
Temperature	10 °C	0.442	0.443	0.446	0.450	0.454	0.458	0.463
	20 °C	0.448	0.449	0.453	0.459	0.464	0.473	0.479
	24 °C	0.452	0.453	0.458	0.465	0.473	0.482	0.489
	30 °C	0.463	0.466	0.473	0.485	0.488	0.497	0.499
	40 °C	0.481	0.484	0.492	0.498	0.499	0.499	0.499
	50 °C	0.491	0.493	0.497	0.499	0.499	0.500	0.500
	60 °C	0.497	0.498	0.499	0.500	0.500	0.500	0.500
	70 °C	0.499	0.499	0.500	0.500	0.500	0.500	0.500
	80 °C	0.500	0.500	0.500	0.500	0.500	0.500	0.500

Disclaimer

The information provided is offered for assistance in application of DuPont laminating interlayer products, but IT DOES NOT CONSTITUTE A WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. Actual performance may vary in particular applications.

The information provided is believed to give adequate estimates of mechanical behavior to aid structural design with laminated glass based upon best engineering judgment and practices but no claims are made as to the accuracy of the results obtained. Users will need to satisfy themselves that the results are reasonable for their purposes. The performance of the final construction should be measured before adoption to meet a specification. Any use of the information provided is the sole responsibility of the user. Furthermore, conclusions drawn from the information provided should be checked against building code requirements in the jurisdiction of the construction.

Because DuPont cannot anticipate or control the many different conditions under which this information and or product may be used, it does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. Users of DuPont products should make their own tests to determine the suitability of each such product for their particular purposes.

NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OR MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH THE INFORMATION REFERS.



The miracles of science™